



PRODUCT INFORMATION • SPECIFICATION GUIDE HDPE ALLOY - Reinforced 20 Mil Cross Laminated

PHYSICAL PROPERTIES AND TYPICAL VALUES	PROPERTY	ASTM TEST METHOD	U.S. VALUE	METRIC VALUE
	Weight	D-751	81 LB/1000 FT ²	39.5 KG/100 M ²
	Thickness	D-2103	20 MIL	0.50 MM
	3" Load @ Yield	D-882	165 LBF	734 N
	3" Load @ Break	D-882	170 LBF	756 N
			2800 PSI	19.3 MPA
	3" Elongation @ Break	D-882	525 %	525 %
	Tongue Tear	D-2261	35 LBF	156 N
	Trapezoidal Tear	D-4533	50 LBF	222 N
	PPT Resistance	D-2582	48 LBF	214 N
	Dart Impact Strength	D-1709 (B)	2.5 LBS	1.14 KG
	Puncture Strength	D-4833	50 LBF	222 N
Permeability	E-96	.0143 Grain/Hr•Ft ² •In.Hg		

- Cross-laminated polyethylene that resists punctures and tears.
- UV stabilized to withstand prolonged exposure to sunlight.
- Reinforced and not prone to environmental stress-cracking (ESC) so it can endure repeated thermal expansion & contraction cycles.

Sales & Procurement Center - Phone No. (907) 562-5755 ~ Fax No. 206.219.3740

WA State Sales - Phone No. (206) 774.8777 ~ Toll Free: 1 (800) 490.5320

GeoCHEM Website: <http://www.geocheminc.com> Contact Us: <http://www.geocheminc.com/contactus.htm>

The information provided herein is based upon data believed to be reliable. All testing is performed in accordance with ASTM standards and procedures. All values are typical and nominal and do not represent either minimum or maximum performance of the product. Although the information is accurate to the best of our knowledge and belief, no representation of warranty or guarantee is made as to the suitability or completeness of such information. Likewise, no representation of warranty or guarantee, expressed or implied, or merchantability, fitness or otherwise, is made as to product application for a particular use.