SG 500



Uni-Axial Knitted Geogrid

STRATAGRID is geogrid reinforcement for soil. These high performance geogrids are constructed of high molecular weight and high tenacity polyester yarns utilizing a complex knitting process and polymer coating provide superior engineering properties. Yarns are precision knitted into a dimensionally stable, uniform network of apertures providing significant tensile reinforcement capacity. STRATAGRID is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in aggressive soil environments (pH range from 3-9).

PROPERTY	TEST METHOD	ENGLISH	METRIC
Ultimate Strength	ASTM D-6637 Method A	6,400 lbs/ft	93.4 kN/m
Creep Limited Strength	ASTM D-5262/D-6992	4,129 lbs/ft	60.3 kN/m
LTDS (SW, SP, SM, SC)	LTDS or Tal	3,412 lbs/ft	49.8 kN/m
LTDS (GP, GW, GM, GC, SW, SP, SM, SC)	LTDS or Tal	3,264 lbs/ft	47.6 kN/m
LTDS (GW, GP, GM, GC)	LTDS or Tal	2,790 lbs/ft	40.6 kN/m
Molecular Weight (min.)	GRI GG8	-	25,000 g/mol
Carboxyl End Group Count (max.)	GRI GG7	-	30 Meg/kg
Aperture Size	Measured	2.45 x 0.95 in	62.2 x 24.1 mm

ROLL SIZE	AREA	WEIGHT
6' x 300'	200 sys	125 lbs
12' x 225'	300 sys	198 lbs

REDUCTION FACTOR	VALUE
RF(id) Soil - 20mm minus, D50 ≤ 0.2mm (SW, SP, SM, SC)	1.10
RF(id) Soil - 25mm minus, D50 ≤ 8mm (GP, GW, GM, GC, SW, SP, SM, SC)	1.15
RF(id) Soil - 50mm minus, D50 ≤ 20mm (GW, GP, GM, GC)	1.35
$RF(d) (3 \le pH \le 9) (PET - CEG < 30, MW > 25,000)$	1.10

SOIL INTERACTION COEFFICIENT	VALUE
Silts/Clay (ML, CL)	0.6 - 0.7
Sandy Silts & Clay (SC,GC)	0.7 - 0.8
Poorly-Graded Sand & Gravel, Silty Sand (GP, GM, SP, SM)	
Well-Graded Gravel, Sand Gravel Mix, Well-Graded Sand (SW, GW)	

This information is provided for reference only and is not intended as a warranty or guarantee. GeoCHEM, Inc. assumes no liability in connection with the use of this information (1/2013).

GeoCHEM, Inc. - Phone: (907) 562.5755 ~ Fax: 206.219.3740

WA State Sales - Phone: (206) 774.8777 ~ Toll Free: 1 (800) 490.5320

http://www.geocheminc.com